

Safety Zone

12 Mil Clear

MECHANICAL PROPERTIES

Thickness	12 mil multi-ply
Tensile Strength at Break	28,500 PSI
Break Strength	336 lb/inch
Elongation at Break	125 %
Peel Strength	7 lb/inch



OPTICAL & SOLAR PROPERTIES

Visible Light Transmitted	83 %
Visible Light Reflected	10 %
Ultra Violet Block	96 %
Total Solar Energy Reflected	11 %
Total Solar Energy Transmitted	74 %
Total Solar Energy Absorbed	15 %
Shading Coefficient	0.9
Total Solar Energy Rejected	22 %