



Hanita Coatings

SECUR-GRIP 4 MIL CLEAR Exterior SR

MECHANICAL PROPERTIES

Structure	4 mil
Tensile Strength at Break	28,500 PSI
Break Strength	112 lb/inch
Elongation at Break	125 %
Peel Strength	7 lb/inch

OPTICAL & SOLAR PROPERTIES

Visible Light Transmitted	86 %
Visible Light Reflected	9 %
Ultra Violet Block	99 %
Total Solar Energy Reflected	9 %
Total Solar Energy Transmitted	78 %
Total Solar Energy Absorbed	13 %
Shading Coefficient	0.96
Total Solar Energy Rejected	19 %